

sawafill[®] 280010

Product information

Type of nonwoven	Nonwoven, thermally and mechanically bonded, progressive construction. Dirty air side coloured blue.
Recommendation for application DIN EN779	G3
Recommendation for application ISO 16890	ISO Coarse
Fibre	Polyester

Technical data

Basis weight NWSP 130.1	130 g/m ²
Thickness without load	13 mm
Flammability DIN 53438	F1/F1/K1

This information is provided in good faith but Sandler cannot guarantee its accuracy or completeness. The end user is advised to evaluate the product and use it only in compliance with all applicable laws and regulations. This is not a specification. Properties are given as typical values.

Packaging/delivery quantities differing from standard might cause a decrease in thickness.

SA 2022-01


sawafill[®] 280010

Technical data

Basis weight
NWSP 130.1

130 g/m²

Initial pressure drop



This information is provided in good faith but Sandler cannot guarantee its accuracy or completeness. The end user is advised to evaluate the product and use it only in compliance with all applicable laws and regulations. This is not a specification. Properties are given as typical values.

Packaging/delivery quantities differing from standard might cause a decrease in thickness.

SA 2022-01